



Europäisches Patentamt
European Patent Office
Office européen des brevets



Publication number:

0 538 683 A1

12

EUROPEAN PATENT APPLICATION

21 Application number: 92117203.7

51 Int. Cl.⁵: C08G 73/10

22 Date of filing: 08.10.92

30 Priority: 25.10.91 US 782923

43 Date of publication of application:
28.04.93 Bulletin 93/17

84 Designated Contracting States:
DE FR GB

71 Applicant: International Business Machines
Corporation
Old Orchard Road
Armonk, N.Y. 10504(US)

72 Inventor: Angelopoulos, Marie
151 Orchard Road, Apt. 3b
Briarcliff Manor, New York 10510(US)
Inventor: Gelorme, Jeffrey Donald
30 Hemingway Street
Plainville, Connecticut 06062(US)

Inventor: Labadie, Jeffrey William
1618 Kamsack Drive
Sunnyvale, California 94087(US)
Inventor: Lewis, David Andrew
451 C Drewville Road
Carmel, New York 10512(US)

Inventor: Swanson, Sally Ann
1566 Ballantree Way
San Jose, California 95118(US)
Inventor: Labianca, Nancy Carolyn
45 High Street
Yalesville, Connecticut 06492(US)


74 Representative: Mönig, Anton, Dipl.-Ing. et al
IBM Deutschland Informationssysteme
GmbH Patentwesen und Urheberrecht
Pascalstrasse 100
W-7000 Stuttgart 80 (DE)

54 Polyamic acid and polyimide from fluorinated reactant


57 Copolyamic acid is obtained from tetracarboxylic acid dianhydride, diamine and a fluorinated diamine and/or fluorinated tetracarboxylic acid dianhydride; and optionally ester or amine salt derivative thereof to obtain radiation sensitive polymer; and low optical high thermally stable polyimide from curing the above polyamic acid and/or derivative thereof.

EP 0 538 683 A1

6F PSPI



Before Polymer Cure: 4 um Imaged polymer lines



After Polymer Cure (Photo Package Burnoff):

BEST AVAILABLE COPY

The present invention is concerned with new copolyamic acids and polyamic derivatives (e.g. - esters, and amine salts) and polyimides derived from curing the copolyamic acids or derivatives thereof. In particular, the present invention is concerned with polyimides that are especially useful as radiation sensitive polymers. The present invention makes possible the formation of polyimides that exhibit high glass transition temperature, low thermal expansion from a photocrosslinkable poly(amic acid) derivative which also displays low ultraviolet light absorption.

Polyimides are currently used to a large extent in microcircuit fabrication as carrier layers and insulating layers in electronic packaging of semiconductor chips and micro-circuitry. When the polyimides are provided on a substrate, such are normally applied as precursors in the polyamic acid form that contains free carboxylic acid groups. For the most part, the fabrication of photopatterned polyimide layers is carried out using non-photoreactive polyimide precursors with the aid of conventional photoresist materials.

In addition, in order to be able to significantly reduce the number of processing steps, there have been some suggestions to directly photopattern photocrosslinkable polyimide precursors. For instance, see U.S. Patents 4,670,535 and 4,778,859.

Of particular importance in the electronics industry are polyimides based upon 3,3',4,4'-biphenyl tetracarboxylic acid dianhydride (BPDA) and p-phenylene diamine (PDA). Such polyimides possess several important properties for such purposes including low solvent uptake, low thermal expansion coefficient (TCE) and high glass transition temperature (Tg). However, developing a photosensitive polyimide system based on a BPDA and PDA backbone is made difficult because of high absorption of the backbone in much of the ultraviolet light region. This high absorption limits the efficiency of any photochemistry occurring at 313, 334, 365, 405 and 436 nanometers mercury lines because of competitive absorption between the backbone and any initiators required for the photochemistry.

Although polyimides have been obtained from 2,2-bis(3,4-dicarboxyphenyl) hexafluoropropane dianhydride and 2,2-bis[4-aminophenyl] hexafluoropropane, these polymers do not possess the types of physical properties needed for use in the electronics industry such as a high glass transition temperature (>350 °C), a low thermal expansion coefficient and high solvent resistance. These polyimides and their related polyimide precursors, however, have much lower absorption in the UV region as compared to polyimides based on BPDA/PDA.

The present invention makes it possible to significantly reduce the UV absorption characteristics of polyimides and radiation crosslinkable polyimide precursors without incurring a concomitant loss to any significant extent of physical properties of the polyimide such as the glass transition temperature and the coefficient of thermal expansion.

The polyimides obtainable by the present invention also exhibit good solvent resistance (e.g. - resistance to swelling and cracking).

In addition, the present invention provides polyimide precursor compositions that exhibit increased solubility and increased flexibility as compared to the rigid BPDA/PDA prior art systems, which, in turn, leads to faster development time and high resolution patterns.

In particular, the present invention is concerned with a copolyamic acid or ester thereof or amine salt thereof from:

- a) tetracarboxylic acid dianhydride,
- b) organic diamine having the formula:




wherein R¹ is a polycyclic aromatic organic diradical in which the aromatic rings may be aromatic, heterocyclic, or directly attached rings; and

c) a co-reactant selected from the group consisting of:

- 1) fluorinated diamine having a formula selected from the group consisting of:

- i)



wherein A is


$C(CF_xH_{3-x})(R^2)$

R^2 is alkyl or aryl or CF_xH_{3-x} ;

x is a whole number integer from 1-3

z is a whole number integer from 0-4; and

ii)




wherein B is a direct bond or

$C(CH_3)_2$; and

y is a whole number integer from 1-4; and

2) fluorinated tetracarboxylic acid dianhydride having the formula



wherein

X^1 is fluorine and each X^2 individually is selected from the group consisting of hydrogen, fluorine and chlorine, R^3 is alkyl, aryl or $C(X^2)_3$; and

3) mixtures of 1) and 2); and

when said co-reactant includes said fluorinated diamine, the molar ratio of said organic amine to said fluorinated diamine is about 9.5:0.5 to about 1:1; and when said co-reactant includes said fluorinated tetracarboxylic acid dianhydride, the molar ratio of said tetracarboxylic acid dianhydride to said fluorinated tetracarboxylic acid dianhydride is about 9.5:0.5 to about 1:1.

In addition, the present invention is concerned with copolyamic acid derivatives such as esters containing monoethylenically unsaturated groups or containing monoacetylenically unsaturated groups, and/or monoethylenically unsaturated or monoacetylenically unsaturated amine salts of the above described copolyamic acids.

A further aspect of the present invention is a copolyimide obtained from curing the above copolyamic acids and/or derivatives thereof.

The present invention is also concerned with radiation sensitive compositions that contain the above copolyamic acids or derivatives thereof. The radiation sensitive compositions will typically also contain an initiator and sensitizer.

A still further aspect of the present invention is concerned with using the above-defined radiation sensitive compositions to fabricate a pattern. The process comprises providing a layer of the radiation sensitive composition and then imagewise exposing selected portions of the layer to actinic radiation to cause crosslinking of the exposed portions. The unexposed portions of the layer are removed to thereby provide the pattern, followed by thermal cure for conversion to the patterned polyimide.


The figure is a SEM illustrating use of the present invention for lithography.

The copolyamic acids or derivatives thereof (polyimide precursors) of the present invention are from a tetracarboxylic acid dianhydride, diamine and fluorinated diamine and/or fluorinated tetracarboxylic acid dianhydride. The polyimide precursors of the present invention exhibit good physical properties, while at the same time, possessing relatively low UV absorption characteristics. In addition, the polyimide precursors of


the present invention possess improved solubility and flexibility which leads to faster development time and high resolution as compared to a rigid BPDA/PDA system.

Polyimides obtained from curing the polyimide precursors can be thermoplastic displaying a T_g, or be absent of a T_g to the decomposition point depending on the composition.

Examples of tetracarboxylic acid dianhydrides are characterized by the following formula:



wherein R is a tetravalent organic radical selected from the group consisting of aromatic, aromatic heterocyclic, and substituted groups thereof. However, the more typical dianhydrides are those in which the R groups have at least 6 carbon atoms characterized by benzenoid unsaturation, i.e., resonating double bonds in an aromatic ring structure, wherein the 4 carbonyl groups of the dianhydride are each attached to separate carbon atoms and wherein the carbon atoms of each pair of carbonyl groups are directly attached to adjacent carbon atoms in a 6-membered benzenoid ring of the R group to provide a 5-membered ring as follows:



Illustrations of dianhydrides suitable for use in the present invention include: pyromellitic dianhydride; 2,3,6,7-naphthalene tetracarboxylic dianhydride; 3,3',4,4'-biphenyltetracarboxylic acid dianhydride; 1,2,5,6-naphthalene tetracarboxylic dianhydride; 2,2',3,3'-biphenyl tetracarboxylic dianhydride; bis (3,4-dicarboxyphenyl) sulfone dianhydride; 3,4,3',4'-benzophenone tetracarboxylic dianhydride; terphenyl dianhydride; and mixtures thereof.


The preferred tetracarboxylic acid dianhydride is 3,3',4,4' biphenyl tetracarboxylic acid dianhydride (BPDA).

Examples of organic diamines are characterized by the formula:



wherein R¹ is a monocyclic or polycyclic aromatic organic diradical in which the aromatic rings may be aromatic, heterocyclic, or directly attached rings, e.g., biphenylene and naphthalene.

The more typical R¹ groups in the diamines are those containing one or more rings, having 6 carbon atoms characterized by benzenoid unsaturation in each ring. Such R¹ groups include



specific examples of some diamines are: p-phenylene diamine;
4,4'-diamino-diphenylamine; benzidine;
4,4'-diamino-diphenyl ether;


1,5-diamino-naphthalene;
 3,3'-dimethyl-4,4'-diamino-biphenyl;
 3,3'-dimethoxy benzidine;
 1,4-bis(p-aminophenoxy) benzene;
 1,3-bis(p-aminophenoxy) benzene;

The preferred diamine employed pursuant to the present invention is p-phenylene diamine.

The dianhydride and diamine are selected such that when used together without the modifications of the present invention would provide a relatively rigid polyimide having a Tg of at least about 320 °C and preferably at least about 350 °C. The dianhydride and diamines employed are free from bridged or linked radicals as R and R¹ in the above formulae for the dianhydrides and diamines, respectively. The presence of such bridged or linked radicals would give the polyimide an undesired degree of flexibility.

The fluorinated diamines that can be employed in the present invention are represented by the following formula:

1)



wherein A is


C(CF_xH_{3-x}) (R²)

R² is alkyl or aryl or CF_xH_{3-x};

x is a whole number integer from 1-3

z is a whole number integer from 0-4; and

2)



wherein B is a direct bond or

C(CH₃)₂; and

y is a whole number integer from 1-4.


Preferred A groups are C(CF₃)₂ and C(CF₃)(phenyl).

The preferred fluorinated diamine is 2,2- Bis [4-aminophenyl] hexafluoropropane.

In order to achieve the results obtained by the present invention when a fluorinated diamine is used, it is essential that the molar ratio of the organic diamine to the fluorinated diamine be about 9.5:0.5 to about 1:1, preferably about 9.5:0.5 to about 7:3, and most preferably about 9:1 to about 8:2.

In addition, the copolyamic acids and derivatives thereof of the present invention can include fluorinated dianhydrides, preferably 2,2 bis (3,4-dicarboxyphenyl) hexafluoropropane dianhydride in place of or in addition to the fluorinated diamine.

Fluorinated tetracarboxylic acid dianhydrides are represented by the formula:



wherein X^1 is fluorine and each X^2 is individually selected from the group consisting of hydrogen, fluorine, and chlorine, and preferably fluorine, R^3 is alkyl, aryl or $C(X^2)_3$.

Preferred linkage groups are $C(CF_3)_2$ and $C(CF_3)(phenyl)$.

Examples of alkyl groups for R^2 and R^3 in the above formulae for the diamine and dianhydride, respectively, include C_1 - C_6 groups such as methyl, ethyl and propyl. An example of an aryl group for R^2 and R^3 in the above formulae for the diamine and dianhydride, respectively, is phenyl.

When a fluorinated dianhydride is employed such is typically present in an amount such that the molar ratio of the tetracarboxylic acid dianhydride to said fluorinated dianhydride is about 9.5:0.5 to about 1:1, preferably about 9.5:0.5 to about 7:3 and most preferably about 9:1 to about 8:2.

The copolyamic acids can be prepared by those techniques used to prepare prior art polyimide precursors such as solution polymerization, typically using about equimolar amounts of the diamine component and the dianhydride component. The dianhydride can be added first to the solvent followed by the addition of a heated solution of the diamines to the dianhydrides. Normally, the temperature of such solution is about $25^\circ C$ to about $50^\circ C$. Alternatively, powdered dianhydride can be added to a solution of the diamines at a temperature of about 0 to about $10^\circ C$.

The reaction is typically carried out under an inert gas atmosphere such as nitrogen. The solvents useful in the solution polymerization are the organic solvents whose functional groups do not react with either of the reactants (the diamines or the dianhydrides) to any appreciable extent. Besides being inert to the system and preferably being a solvent for the polyamide-acid, the organic solvent must be a solvent for at least one of the reactants, preferably for both of the reactants. To state it another way, the organic solvent is an organic liquid other than either reactant or homologs of the reactants that is a solvent for at least one reactant, and contains functional groups, the functional groups being groups of other than mono-functional primary and secondary amino groups, hydroxyl or thiol groups, and other than the monofunctional dicarboxylanhydro groups.

Suitable solvents include N,N-dialkyl carboxylamides such as N,N-dimethyl-formamide, N,N-dimethyl-acetamide, N,N-diethylformamide, N,N-diethylacetamide, N,N-dimethylmethoxyacetamide, N-methyl caprolactam; dimethylsulfoxide, N-methyl-2-pyrrolidinone, tetramethyl urea, pyridine, dimethylsulfone, hexamethylphosphoramide, tetramethylene sulfone, formamide, N-methylformamide, butyrolactone. The solvents can be used alone, in combinations of solvents, or in combination with poorer solvents such as benzene, ethyl acetate, tetrahydrofuran, diglyme, benzonitrile, dioxane, xylene, toluene and cyclohexane. The preferred solvent is N-methyl-2-pyrrolidinone.

The polymerization is usually carried out for a period of time sufficient that the molecular weight of the polymer is such that the inherent viscosity of the polymer is at least 0.25 dl/g and preferably about 0.35 to about 0.6 dl/g. The inherent viscosity is measured at $35^\circ C$ at a concentration of 0.5% by weight of its polymer in N-methyl pyrrolidinone.

When the polyimide precursors are to be used in radiation sensitive compositions, a polyimide precursor with a monoethylenically or monoacetylenically unsaturated group can be prepared directly from the poly(amic acid) by quaternization with an amine containing a vinyl group or monoacetylenically unsaturated group, respectively, such as dimethylaminomethylmethacrylate, and aminostyrene. Alternatively a poly(amic ester) with a suitable monoethylenically or monoacetylenically unsaturated group can be prepared by reaction of typically about 2 moles of a substituted monoethylenically or monoacetylenically unsaturated compound containing an alcohol functionality with the dianhydride forming a half ester/acid monomer, followed by conversion to the diacyl chloride or imidazolid, followed by polymerization with a diamine. Examples of alcohols are hydroxyethylmethacrylate, hydroxypropylmethacrylate, hydroxyethylacrylate, and N-(hydroxymethyl) acrylamide, and propargyl alcohol.

The reaction of the polyamic acid with an appropriate monoethylenically or monoacetylenically unsaturated amine is typically carried out by reacting the polyamic acid directly with the amine at room

temperature for about 12 to about 24 hours. Suitable amines are 3-allylamines, propargyl amines, and aromatic amines such as dimethylaminomethylmethacrylate, and aminostyrene.

In the case of the polyamic ester, the dianhydride is reacted with a hydroxy terminated ester of a monoethylenically or monoacetylenically unsaturated carboxylic acid such as 2-hydroxyethylmethacrylate, to convert each anhydride unit to an ester acid unit.

The resulting bis (ester acid) is converted into a reactive monomer by conversion of the acid groups into a reactive carboxyl species such as acid chlorides or imidazolides, that are polymerized with the diamine. When employed the unsaturated esters are present in an amount of 50 to 100%, preferably about 75-100%, the balance made up with unreactive esters, such as methyl or ethyl.


The copolyamic acids of the present invention can be cured to polyimides by heating to temperatures of about 170° C to about 400° C and preferably about 250° C to about 400° C.

In addition, the monoethylenically substituted ester and salt derivatives of the copolyamic acids can be crosslinked by subjecting such to actinic light such as visible light, ultraviolet light, e-beams, ion beams or x-rays.


When the compositions of the present invention are to be used in radiation sensitive composition, the compositions typically include radiation sensitive initiator and sensitizer.

However, when e-beam or x-ray is the radiation source, the initiator and sensitizer may not be necessary.


The preferred initiators are:



Irgacure 907® and



and Ciba Geigy CG 25-369®




Irgacure 651®

Other initiators include:

bis(dialkylamino) benzophenones, e.g., Michler's ketone and 4,4'-bis(diethylamino)benzophenone; other ketones, e.g. 2,5-bis(4'-diethylaminobenzal)cyclohexanone, 2,6-bis(4'-dimethylaminobenzal)-4-methylcyclohexanone, 2,6-bis(4'-diethylaminobenzal)-4-methylcyclohexanone, 4,4'-bis(dimethylamino)chalcone, 4,4'-bis(diethylamino)chalcone, p-dimethylaminocinnamylideneindanone, p-dimethylaminobenzylideneindanone, 2-(p-dimethylaminophenylvinylene)benzothiazole, 2-(p-dimethylaminophenylvinylene) isonaphthothiazole, 1,3-bis(4'-dimethylaminobenzal)acetone, 1,3-bis-carbonylbis(7-diethylaminocoumarin); ethanolamine derivatives represented by the following formula S(A); and mercapto-containing aromatic heterocyclic compounds.


S (A)




In this formula, R is hydrogen, an aliphatic residue which may have hydroxyl, or an aromatic residue.

The ethanolamine derivatives include, for example, N-phenyldiethanolamine, N-phenylethanolamine, and N-phenyl-N'-ethylethanolamine. The mercapto-containing aromatic heterocyclic compounds include, for example, 2-mercaptobenzimidazol, 2-mercaptobenzothiazole, and 1-phenyl-5-mercapto-1H-tetrazole.


Examples of suitable sensitizers are the thioxanthone derivatives such as those represented by the formula:



wherein R is isopropyl or propoxy, and those represented by the formula:



wherein R¹ is -C(CH₃)₂CH₂C(CH₃)₃,



-CH₂CH₂OH, -CH₂CH₂N(CH₃)₂, -N(CH₃)₂, -CH₂CH₂SO₃⁻Na⁺, -CH₂CH₂CH₂N(CH₃)₂, -CH₂CH₂N(C₂H₅)₂, -CHCH=CH₂, -CH₂-C≡CH, and -CH(CH₃)₂.

The initiator is usually present in the composition in amounts of about 1% to about 5%, and preferably about 2.5% to about 3% by weight based upon the polyimide precursor.

The sensitizer is usually present in the composition in amounts of about 1% to about 5% and preferably about 2.5% to about 3% based upon the polyimide precursor.

In addition, radiation sensitive compositions will normally be applied as a solution of polyimide precursor and may but not necessarily include one or more reactive diluents.

Suitable reactive diluents include polyethylenically unsaturated compounds that are capable of reacting upon exposure to radiation such as ultraviolet light, and usually those that contain terminal ethylenic groups. Such compounds include unsaturated esters of polyols and especially esters of the methylene carboxylic acid such as ethylene diacrylate; diethylene glycol diacrylate; glycerol diacrylate; glycerol triacrylate; ethylene dimethacrylate; 1,3-propylene dimethacrylate; 1,2,4-butene triol trimethacrylate; 1,4-benzenediol dimethacrylate; pentaerythritol tetramethacrylate; 1,3-propane diol diacrylate; 1,6-hexane diol diacrylate; the bis-acrylates and methacrylates of polyethylene glycols of molecular weight 200-500; trimethylol propane

triacrylate; 2-ethyl-2-(hydroxymethyl)-1,3propanediol triacrylate; pentaerythritol triacrylate; unsaturated amides such as those of the methylene carboxylic acids and especially those of alpha, omega-diamines and oxygen-interrupted omega-diamines such as methylene bisacryl and bismethacrylamide; diethylene triamine tris-methacrylamide; bis-(methacrylamidopropoxy) ethane; bis-methacrylamidoethyl methacrylate; N-[(B-hydroxyethyloxy) ethyl] acrylamide; vinyl-esters such as divinyl succinate; divinyl adipate; divinyl phthalate, divinyl terephthalate, divinyl benzene-1,3-disulfonate, and divinyl butane-1,4-disulfonate; and unsaturated aldehydes such as sorbaldehyde.

The composition will typically contain about 1% to about 10% and preferably about 2% to about 8% by weights of the reactive diluent based upon the weight of copolyamic acid or derivative thereof.

When compositions of the present invention are to be used in forming a pattern, the exposure to the actinic radiation is imagewise exposure of selected portions using contact or projection techniques. The unexposed portions are then removed such as by dissolution in a developer such as N-methylpyrrolidinone, butyrolactone, diglyme, mixtures of N-methylpyrrolidinone and diglyme and mixtures of N-methylpyrrolidinone and xylene. When the actinic radiation is ultraviolet light or x-rays, a mask is employed to define the pattern. On the other hand, when the actinic radiation is e-beam, direct pattern writing is used without employing a mask.

The developing normally takes about 3 to about 6 minutes and preferably about 3 to about 4 minutes.

In addition, polymers of the present invention can be used as low loss optical waveguides and in compression molding operations. Polymers of the present invention also exhibit elongation properties (e.g. - 25%) above the T_g.

The following non-limiting examples are presented to further illustrate the present invention:

Example 1

A 3 neck flask is flame dried, evacuated and placed under a nitrogen atmosphere. To this flask are added with stirring about 15 grams (0.051 moles) of 3,3',4,4'-biphenyl tetracarboxylic acid (BPDA) dianhydride to 100 ml of N-methyl pyrrolidinone to produce a dianhydride suspension.

In a separate flask about 4.96 grams (0.0459 mole) of phenylenediamine (PDA) and about 1.7 grams (0.0051 moles) of 2,2-bis (4-aminophenyl) hexafluoropropane are added to about 100 ml of N-methylpyrrolidinone at a temperature of about 50 °C to produce a diamine solution.

The diamine solution is then added to the suspension of the dianhydride.

The mixture is reacted under nitrogen for about 12 hours. The polymer obtained exhibits the properties reported below in Table 1.

Example 2

Example 1 is repeated except that the molar ratio of the PDA to fluorinated diamine is 4:1. The results are reported in Table 1 below.

Example 3

Example 1 is repeated except that the molar ratio of the PDA to fluorinated diamine is 7:3. The results are repeated in Table 1 below.

Example 4

Example 1 is repeated except that the molar ratio of the PDA to fluorinated diamine is 1:1. The results obtained are reported in Table 1 below.

Comparison Example 5

Example 1 is repeated except that no fluorinated diamine is employed. The results obtained are reported in Table 1 below.

Table 1

Example No.	Absorption at 365 nm	Glass Transition temperature (Tg)	Thermal Expansion Coefficient (TCE)
1	0.60	>400	17
2	0.48	389	29
3	0.28	370	34
4	0.22	----	--
5	1.16	>400	5

As evident from the above results, even a 10 molar % of the fluorinated diamine reduces the absorption by a half at 365 nm, the glass transition temperature for the materials of the present invention are not significantly lowered, nor is the TCE significantly increased. The polymers having 20 and 30 molar % of the fluorinated diamine also have acceptable TCE values and Tg.

The polymers of the present invention when heated above the Tg can be extended by at least about 25%; while the polymers without the fluorinated diamine undergo very little extension (0.8%). The extendability of the polymers of the present invention suggest that such would be suitable for compression molding.

Example 6

A 3 neck flask is flame dried, evacuated and placed under a nitrogen atmosphere. To this flask are added with stirring about 6.8 grams (0.023 moles) of BPDA and 10.3 (0.023 moles) of 2,2 bis-(3,4dicarboxyphenyl)hexafluoropropane dianhydride to about 100 ml of N-methyl-pyrrolidinone to produce a dianhydride suspension. In a separate flask, about 5 grams (0.046 moles) of PDA is added to about 100 ml of N-methylpyrrolidinone at a temperature of about 50° C to produce a diamine solution. The diamine solution is added to the dianhydride suspension. The mixture is reacted under nitrogen for about 12 hours. The results are similar to those of Example 4.

Example 7

A three-necked flask is dried, and placed under an atmosphere of dry air. To this flask are added about 239.8 grams (0.815 moles) of BPDA, about 224.1 grams (1.722 moles) of 2-hydroxyethylmethacrylate, about 0.40 grams benzoquinone, about 34.86 grams (0.00353 mole) triethylamine and about 800 ml chloroform. This mixture is stirred and refluxed overnight to produce the diethylmethacrylate ester-diacid derivatives of BPDA. The chloroform is removed under reduced pressure and the resulting oil is triturated with hexane to remove excess hydroxyethylmethacrylate. The diester-diacid is dissolved in about 800 ml ethylacetate and about 0.4 grams benzoquinone is added. This solution is cooled in an ice bath to about 5° C and about 393.2 grams (3.098 moles) of oxalyl chloride is added slowly keeping the temperature below 10° C. The reaction is allowed to proceed at room temperature overnight and then warmed to about 45° C for about 1 hour to complete the preparation of the diester-diacyl chloride derivatives of BPDA. Excess oxalyl chloride is removed under reduced pressure, triethylamine hydrochloride is removed by filtration and the diester-diacyl chloride is added slowly to a solution of about 76.96 grams (0.712 moles) of p-phenylenediamine (PDA) and about 26.43 grams (0.0791 moles) of 2,2-bis(4-aminophenyl)hexafluoropropane in about 254.1 grams (3.212 moles) pyridine and about 2 l of N-methylpyrrolidinone at a temperature of about 5° C. The resulting polyamic ester can be isolated by precipitation in water and the yield is about 450 grams.

Example 8

A composition containing about 35% by weight of the copolymer prepared along the lines of Example 1 in N-methyl-2-pyrrolidinone, about 3% by weight of Ciba-Geigy CG 25-369®; about 3% by weight of propoxythioxanthone sensitizer, and about 7.5% of 2-ethyl-2-(hydroxymethyl)1,3propane diol triacrylate diluent is coated onto a substrate by spinning. The composition is post-apply baked at about 80° C for about 4 minutes on a hotplate to provide a coating of about 17 µm thick. The coating is then exposed to 404 nanometer with a dose of about 400 millijoules. The coating is then post-expose baked at about 80° C for about 2 minutes on a hotplate and dip developed using a composition of about 90% diglyme and 10% N-methyl-2-pyrrolidinone for about 3 minutes followed by a methyl ethyl ketone rinse. Four µm lines are


resolved in the 17 μm thick film. The figure is a SEM illustrating the resolution of this example. The coating is post-cured to about 400 °C to provide a 7.5 μm thick film.

Claims

1. A copolyamic acid from

- a) tetracarboxylic acid dianhydride,
- b) organic diamine having the formula: $\text{H}_2\text{N}-\text{R}^1-\text{NH}_2$; wherein R^1 is a polycyclic aromatic organic diradical selected from the group consisting of aromatic, heterocyclic, and directly attached rings; and
- (c) a co-reactant selected from the group consisting of:
 - (1) fluorinated diamine having a formula selected from the group consisting of:

i)



wherein A is


$\text{C}(\text{CF}_x\text{H}_{3-x}) (\text{R}^2)$

R^2 is selected from the group consisting of alkyl, aryl and $\text{CF}_x\text{H}_{3-x}$;

x is a whole number integer from 1-3

z is a whole number integer from 0-4; and

ii)




wherein B is a direct bond or

$\text{C}(\text{CH}_3)_2$; and

y is a whole number integer from 1-4; (2)


fluorinated tetracarboxylic acid dianhydride having the formula




wherein X^1 is fluorine and each X^2 individually is selected from the group consisting of hydrogen, fluorine and chlorine; R^3 is selected from the group consisting of alkyl, aryl and $\text{C}(\text{X}^2)_3$; and (3) mixtures of (1) and (2); and when said co-reactant includes said fluorinated diamine, the molar ratio of said organic diamine to said fluorinated diamine is about 9.5:0.5 to about 1:1; and when said co-reactant includes said fluorinated tetracarboxylic acid dianhydride,

the molar ratio of said tetracarboxylic acid dianhydride to said fluorinated tetracarboxylic acid dianhydride is about 9.5:0.5 to about 1:1.


2. The copolyamic acid of claim 1 wherein said tetracarboxylic acid dianhydride is selected from the group consisting of pyromellitic dianhydride; 2,3,6,7-naphthalene tetracarboxylic dianhydride; 3,3',4,4'-biphenyltetracarboxylic dianhydride; 1,2,5,6-naphthalene tetracarboxylic dianhydride; 2,2',3,3'-biphenyl tetracarboxylic dianhydride; bis (3,4-dicarboxyphenyl) sulfone dianhydride; 3,4,3',4'-benzophenone tetracarboxylic dianhydride; terphenyl dianhydride; and mixtures thereof with terphenyl dianhydride being preferred, said organic diamine is selected from the group consisting of p-phenylene diamine; 4,4'-diaminodiphenylamine; benzidine; 4,4'-diamino-diphenyl ether; 1,5-diamino-naphthalene; 3,3'-dimethyl-4,4'-diamino-biphenyl; 3,3'-dimethoxy benzidine; 1,4-bis(p-aminophenoxy) benzene; 1,3-bis(p-aminophenoxy) benzene; and mixtures thereof with p-phenylene diamine being preferred.
3. The copolyamic acid of claim 1 wherein the molar ratio of the organic diamine to the fluorinated diamine and the molar ratio of the tetracarboxylic acid dianhydride to the fluorinated tetracarboxylic acid dianhydride is about 9:1 to about 8:2.
4. The copolyamic acid of claim 3 wherein said fluorinated diamine is 2,2-bis[4-aminophenyl] hexafluoropropane.
5. A copolyamic ester derivative of the copolyamic acid of claim 1, being obtained by reacting the copolyamic acid with a member selected from the group consisting of dimethylaminomethylmethacrylate, aminostyrene, hydroxyethylmethacrylate, hydroxypropylmethacrylate, hydroxyethylacrylate, N-(hydroxymethyl) acrylamide and propargyl alcohol, and mixtures thereof.
6. The copolyamic ester derivative of claim 5 wherein said ester is a monoethylenically or monoacetylenically unsaturated carboxylic ester derivative.
7. The copolyamic amine salt derivative of the copolyamic acid of claim 1 being obtained by reacting the copolyamic acid with a member selected from the group consisting of 3-allylamines, propargyl amines, aromatic amines, and mixtures thereof.
8. The copolyamic acid of claim 1 wherein said fluorinated tetracarboxylic acid dianhydride is 2,2 bis(3,4-dicarboxyphenyl) hexafluoropropane.
9. A copolyimide from curing the polyamic acid of claim 1 or an ester derivative or amine derivative thereof.
10. The copolyamic acid of claim 1 wherein the molar ratio of the organic diamine to the fluorinated diamine and the molar ratio of the tetracarboxylic acid dianhydride to the fluorinated tetracarboxylic dianhydride is about 9.5:0.5 to about 7:3.
11. The copolyamic amine salt derivative of claim 7 wherein said aromatic amine is selected from the group consisting of dimethylaminomethylmethacrylate, aminostyrene, and mixtures thereof.
12. A radiation sensitive composition containing:
 - A. The copolyamic acid of claim 1 or ester derivative or amine salt derivative thereof;
 - B. Photosensitive initiator; and
 - C. Sensitizer.
13. The composition of claim 12 wherein said initiator is



or



and is present in amounts of about 1% to about 5%, and said sensitizer is represented by the formula:




wherein R is isopropyl or propoxy and is present in amounts of about 1% to about 5%.

14. The composition of claim 12 which further includes a reactive diluent said reactive diluent being selected from the group consisting of ethylene diacrylate; diethylene glycol diacrylate; glycerol diacrylate; glycerol triacrylate; ethylene dimethacrylate; 1,3-propylene dimethacrylate; 1,2,4-butene triol trimethacrylate; 1,4-benzenediol dimethacrylate; pentaerythritol tetramethacrylate; 1,3-propane diol diacrylate; 1,6-hexane diol diacrylate; the bis-acrylates and methacrylates of polyethylene glycols of molecular weight 200-500; trimethylol propane triacrylate; 2-ethyl-2-(hydroxymethyl)-1,3 propanediol triacrylate; pentaerythritol triacrylate; unsaturated amides of the methylene carboxylic acids; diethylene triamine trimethacrylamide; bis-(methacrylamidopropoxy) ethane; bis-methacrylamidoethyl methacrylate; N-[(B-hydroxyethoxy) ethyl] acrylamide; vinyl-esters; and unsaturated aldehydes with trimethylol propane triacrylate or 2-ethyl-2-(hydroxymethyl)1,3 propanediol triacrylate being preferred.


15. A process for forming a pattern which comprises providing layer of a radiation sensitive composition of claim 12 imagewise exposing selected portions of said layer to actinic radiation especially from ultraviolet light, e-beams or x-rays to cause crosslinking of the exposed portions and removing the unexposed portions of said layer to thereby provide said pattern.

16. The process of claim 15 wherein the unexposed portions are removed by dissolution in a solvent.

6F PSPI



Before Polymer Cure: 4 um imaged polymer lines



After Polymer Cure (Photo Package Burnoff):

BEST AVAILABLE COPY



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 92 11 7203

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. CL.5)
A	EP-A-0 361 413 (HOECHST CELANESE) ----		C 08 G 73/10
A	EP-A-0 354 360 (HOECHST CELANESE) ----		
A	EP-A-0 354 361 (HOECHST CELANESE) ----		
A	US-A-4 876 329 (W.L. CHIANG et al.) ----		
A	US-A-5 021 540 (A. LEONE-BAY et al.) -----		
			TECHNICAL FIELDS SEARCHED (Int. CL.5)
			C 08 G
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 29-01-1993	Examiner LEROY A J
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons ----- & : member of the same patent family, corresponding document	

EPO FORM 1500 (03.82) (P0401)

THIS PAGE BLANK (USPTO)